

## Product Information:

### Generic Type:

Waterborne acrylic

**General Properties:** A decorative nano stain Technology for concrete surfaces. Beton Betone CF Colors is water submersible, alkali, weather and UV light resistant. These stains require a top coat and are compatible with solvent based, water-based, single and two component products, including but not limited to urethanes, acrylics and epoxy sealers.

**Warning:** Beton Betone CF Colors is not compatible with Methyl Methacrylate or penetrating (e.g. sodium silicate) sealers.

- Compatible with neutralized acid-based stains
- Compatible with overlays, as a topical stain and as integral color
- Low Odor
- Fast Air Dry
- Overnight Deliverable – no Red Label
- Low VOC
- Interior and Exterior application

**Recommended Use:** A user-friendly stain for cured concrete slabs (28 days) and other porous substrates. May be applied over sealed surfaces (refer to Application Instructions).

**Not recommended for:** Non-porous substrates (e.g. metal, resin, fiberglass) when submerged in water or exposed to severe weather conditions.

**Colors:** Three different "Series" give the applicator a wide range of affects that they may obtain. All the colors in the Color Floor line are totally compatible with one another in both the dry and wet stage.  
**Classic Series:** can be used for applications that range from high hide to transparent variegated appearance.

**Old World Series:** remain transparent even with multiple coats — appear very similar to acid stains.

**Bright Light Series:** are high-chroma, intense colors for accenting or artistic differentiation.

**Color Retention:** All the colors formulated for Beton Betone CF Colors have been specially selected to produce the most durable lightfast and alkali resistant coatings available:

Pigment	Alkali Resistance	Ultra-violet Light Resistance
Carbon Black	Excellent	Excellent
Titanium White	Excellent	Excellent
Iron Oxide	Excellent	Excellent
Phthalo Blue	Excellent	Excellent
Phthalo Green	Excellent	Excellent

### Typical Chemical Resistance:

Exposure	Concentrate	Dilute (10%)
Acids	Good	Excellent
Alkalis	Excellent	Excellent
Solvents		
Aliphatic	Good	Good
Aromatic	Good	Good
Ketones	Poor	Poor
Salt	Excellent	Excellent
Water	Excellent	Excellent

### Coverage:

Package Size	Coverage
1 gallon	200-400 SQ FT

Note: Coverage depends on surface porosity, profile and desired appearance

### Taber Abrasion Resistance Test

#### ASTM D 4060-95:

Performed by independent laboratory, Architectural Testing, Inc.

Abrasion resistance values of Beton Betone CF Colors are comparable to acid-based stain.\*

Full report of Architectural Testing, Inc.'s Taber Abrasion Resistance Test is available upon request.

## Product Information:

### Volatile Organic Content:

<i>Note: V.O.C. varies with color</i>		Calculated EPA Method 24	Per Actual Gallon
As supplied	lbs/gal g/l	1.19 - 1.4 142.6 - 164.5	.083 - .088 9.97 - 10.5

### Recommended Dry Film Thickness per Coat:

<1 mil

**Storage Conditions:** 40-110°F

### Shelf Life:

Unopened Container	3 months
--------------------	----------

**Color:** See Beton Betone CF Color Chart.

**Gloss:** Eggshell

### Ordering Information:

Prices may be obtained from Beton Betone Products, Sales Representative or local Beton Betone Decorative Concrete Products Dealer.

### Flash Point:

Beton Betone CF Colors >212°F (100°C)

Upon information, belief and to the best of our knowledge, the information contained herein is true and accurate as of the date of issuance of this particular product and any and all information conveyed, expressed or implied is subject to change without prior notice. We guarantee our products to conform to Beton Betone Products' quality control mechanisms, but not to any other standards. We assume no responsibility for coverage, performance or injuries resulting from use, misuse or uses not described in any promotional materials. Promotional materials are not a supplementation to any contract or expand any term or condition of the product purchase agreement, if any is reduced to writing. Liability, if any, is limited to replacement of the purchased product upon presentation of valid sales receipt or invoice, and no damages for any consequential, liquidated or other damages are provided under this Limitation of Liability and Limited Warranty.

NO OTHER WARRANTY OR GUARANTY OF ANY KIND IS MADE BY BETON BETONE PRODUCTS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. DO NOT PURCHASE AND USE THIS PRODUCT IF YOU HAVE NOT AGREED TO THE ABOVE TERMS.

beton betone is a trade name, anywhere in this document is written beton betone the intention is also to nichsey haeez shivock vyizom nadlan ltd

## Application Instructions:

These instructions are not intended to show product recommendations for specific service. They are issued as an aid in determining correct surface preparation, mixing instructions and application procedure. These instructions should be followed closely to obtain the maximum service from the coatings.

**Area Preparation:** Be sure to mask or cover all areas that are not intended to be stained including but not limited to door frames, doors, walls and windows.

**Surface Preparation:** Whether new or old concrete, the surface preparation phase of "Staining a Concrete Floor" should be viewed as the most important. Proper floor preparation results in the stains longevity, minimizes potential failures and creates the best environment for an aesthetically pleasing work of art. In short, the more detail and time allotted to this phase of the project will dramatically affect the appearance and durability of the finished floor.

The surface must be free of all foreign materials that would inhibit the absorption of Beton Betone CF stain. Foreign materials include, but are not limited to grease, dirt, glue, previous coatings, and sealer\*.

\*Beton Betone CF Colors can be applied to previously sealed surfaces. The process is described in "Previously Sealed Surfaces".

Do not use an acid etch as a cleaning method. Surface preparation is required for both newly cured or old concrete.

### Horizontal Application: Exterior-broom finish

- 1) Broom finishes may result in high profiles or peaks in the substrate which erode faster than the remaining substrate. Remove these unstable sections by simply running an ice scrapper or other metal object over the substrate. Extract debris from substrate. This step will enhance the longevity and durability of the install.
- 2) Apply Beton Betone Profiler Green Clean following the instructions

### for Exterior & Interior Exterior & Interior

- 1) Remove paint, adhesives and loose particulates from the intended application surface.
- 2) Liberally apply Beton Betone Profiler Green Clean to a 20 x 20 foot section of the substrate with ½ inch nap roller cover.
- 3) Allow the gel to remain on the substrate for 20 minutes.

Interiors – use of power wash is not applicable.

4) Agitate Beton Betone Profiler Green Clean utilizing a floor buffer (small area) or an auto-scrubber (large area) equipped with brush attachments while rinsing with clean water.

5) Extract material utilizing a wet/dry vacuum or lower the squeegee uptake bar on the auto-scrubber. Continue to flush and agitate the substrate until the rinse water is clear and surface is free of gel residue. Areas that can be pressure washed:

6) Remove zCleaning from the surface using a power washer\* with overlapping line patterns.

7) Allow the area to dry adequately before performing a Tape Test. Upon the completion of a successful Test begin the application of Beton Betone CF Stains.

\* Power wash = 0 degree rotating nozzle with 12,000 work units (Work Units = Gallons per Minute x PSI)

Interior

If additional profile is desired, reapply Beton Betone Profiler § following the pre 5 us directions.

### Grinding:

- 1) 1st Pass = 40 grit metal bonded diamonds (or comparable) if the surface requires (e.g. adhesives, profile irregularities)
- 2) 2nd Pass = 150 grit metal bonded diamonds (or comparable).
- 3) Inspect the substrate for scratch patterns created by the grinding process. If a scratch pattern exists, continue the grinding process by increasing the grit of the diamond. Wet grinding must be used with resin bonded diamonds to avoid transfer of the resin to the substrate.

### Dry Grinding:

- 3) Remove excess dust with vacuum.
- 4) Remove remaining dust and particulate with microfiber pad. A minimum of 3-4 passes over the substrate with a new/clean micro-fiber mop per pass will remove residual dust. The use of an auto-scrubber with brush attachment in conjunction with clean water can also be used to extract particulate. Continue to clean substrate until extracted water is clear.

### Wet Grinding:

- 3) Remove slurry from floor via wet vacuum or autoscrubber with brush attachment in conjunction with clean water.
- 4) Continue to clean substrate until extracted water is clear. Perform Tape Test once substrate is prepared and dry.

## Application Instructions:

**Tape Test:** A tape test will help determine the effectiveness of the cleaning process. After the floor has been thoroughly scrubbed, rinsed and allowed to dry; apply several 1 foot strips of high quality 2" packaging tape to various locations on the floor. Aggressively press the tape onto the floor with the heel of your hand. Fold one end of the tape into itself and pull it off of the floor as vigorously as possible. Examine the adhesive layer in a bright light looking for residue that was pulled from the floor. Little to no dust or other foreign particles should be visible. Areas with visible foreign material need to be scrubbed and rinsed again until the surface is free of these contaminants.

### Application Directions:

	Material	Surface	Ambient	Humidity
Best	60-90°F	65-85°F	65-90°F	10-60%
Minimum	45°F	45°F	45°F	0%
Maximum	105°F	110°F	110°F	80%

**Application Method:** To achieve a natural variegated appearance, Beton Betone CF Colors should be applied by creating a mist via an airless sprayer, High Volume Low Pressure (HVLV) sprayer, production gun, pump sprayer or trigger spray bottle. The variegation is the result of the specific gravities of the pigments as well as the absorption rate of the application surface. Roller application methods force absorption resulting in mechanical lines.

**Brush/Sea Sponge Application:** For application areas where coverage and product control is warranted, apply Beton Betone CF Colors with a sea sponge or traditional bristle brush (e.g. corners and walls) Using this method of application may result in the appearance of mechanical lines.

**Secondary/Highlight Color:** To achieve increase color depth or mottled appearance. A secondary or highlight coat can be applied as soon as initial Beton Betone CF Color is dry to the touch (approximately 15 minutes).

Note: All Beton Betone CF Colors are compatible, thus can be mixed, sprayed simultaneously and layered to achieve a desired appearance.

**Previously Sealed Surfaces:** After cleaning the previously sealed surface, apply Beton Betone CF Colors via an airless sprayer or HVLV (this application will atomize the stain) to a small, out of the way test section of the sealed surface. Allow the stain to dry (15-20 minutes). Test for adhesion by running your hand over the stained surface. If you are unable to rub the stain off, the stain has achieved adhesion. Apply Beton Betone CF Colors stain to the remaining areas. Allow a 24 hour drying period before applying a clear sealer over Beton Betone CF Colors.

### Dry Times: (optimal)

Temperature	Relative Humidity	Dry to the Touch	Final Cure/ Sealer Coat
70°F	30%	15-20 min	24 hours

Note: High humidity and lower temperatures will lengthen dry and cure times. Dry time can be shortened by increasing temperature and airflow. Proper adhesion will develop with 24 hour cure time.

**Clean Up:** Immediately clean up work area and tools with water while stains are still wet.

**Floor Protection:** Use paper and/or cardboard to protect stained and sealed floor from other trades or during a move. Do not use tape on a sealed surface until sealer is fully cured. A good rule is 30 days for a sealer to fully cure.